

PRODUCT DESCRIPTION

APF CASTORCRETE® TC is a squeegee-applied cementitious polyurethane topcoat installed at 10 mils (0.25 mm) to 20 mils (0.5 mm). It is resistant to impact and abrasion, and stands up to steel wheeled cart traffic. It resists hot cooking oils, animal fats, and many solvents. APF CASTORCRETE® TC has been formulated to compensate for the difference in the coefficient of thermal expansion of concrete and will resist constant service temperatures up to 180°F (93°C).

APF CASTORCRETE TC is a rapid turnaround flooring solution to minimize downtime. APF CASTORCRETE TC is installed as a one-step system urethane cement top coat to create uniformity of performance and appearance in heavy duty CastorCrete mortar systems.

ADVANTAGES

- Resistant to sanitizing chemicals, hot water, steam
- Capable of resisting extreme thermal cycling
- Easy to clean, sanitary

USES

- Food & Beverage Manufacturing
- Meat, Poultry, Fish Processing
- Commercial Kitchens
- Pharmaceutical

COLORS

Available in 5 Standard Colors

PACKAGING

Supplied in complete A+B+C (color pack)+D (aggregate) - 1.75 Gallon (19 lb) complete mixed units. Use only as complete mixed unit, do not break down into partial mixes.

COVERAGE

Floor Thickness	Coverage Per 19 lb Kit
10 mils (0.25 mm)	280 sq ft (26.0 m ²)
16 mils (0.41 mm)	175 sq ft (16.25 m ²)
20 mils (0.5 mm)	140 sq ft (13.0 m ²)

TECHNICAL DATA

Compressive Strength ASTM C579	8,500 psi
Tensile Strength ASTM C307	1,550 psi
Flexural Strength ASTM C580	2,700 psi
Shore D Hardness ASTM D2240	75 - 80
Tabor Abrasion (1000 gm. load 1000 cycles, CS 17 wheel)	32 mg Loss
Thermal Compatibility with Concrete ASTM C884	Passes
Coefficient of Thermal Expansion ASTM C513	1.1 x 10 ⁻⁵ in/in/°F minimum
VOC	<1 g/l
Flammability when Bonded to Concrete ASTM D635	Self-Extinguishing
Standard Version	Dry to touch ~12 Hours
	Full Service ~24 - 36 Hours

Higher temperatures will shorten cure time. Lower temperatures will increase cure time.

SURFACE PREPARATION

Concrete must be cured for at least 7 days and be clean, structurally sound, and free of wax, loose paint, or curing compounds. Concrete should be properly prepared to achieve a minimum surface texture of ICRI 3. Refer to ICRI Technical Guidelines 310-330 *Selecting and Specifying Concrete Surface Preparation for Sealers, Coatings, Polymer Overlays, and Concrete Repair*. Acid etching is not recommended and will void Manufacturer's warranty. Carefully follow the guidelines listed in the Arizona Polymer Flooring published application instructions available at www.apfepoxy.com.

Vacuum prepared concrete surface to remove all dust. Do not apply to previously coated surfaces; apply directly to concrete except when priming is necessary. Key-ways must be cut 1/4-inch (6.3 mm) deep by 3/16-inch (4.8 mm) wide, 6-inch (15.2 cm) from all perimeter walls, machinery pedestals, and both sides of all control joints, and at regular intervals spaced 10 feet (3 m) to 12 feet (3.7 m) apart throughout the flooring system.

SURFACE PREPARATION (Cont.)

All floor drains, penetrations, transitions and termination points must have a 1/4-inch (6.35 mm) deep by 1/4-inch (6.35 mm) wide key-way.

Never feather edge APF CastorCrete® TC, always turn it into a key-way.

MIXING

Pour entire contents of parts A, B, and C (color pack) into mixing container and mix for 30 seconds. While mixing, slowly add part D (aggregate). After all of the components are fully incorporated, mix for an additional 30 seconds. Mixing should be done with a heavy-duty drill and whip. Place mixed material immediately. Multiple mixing containers are recommended to ensure an adequate supply of fresh material.

Do not thin product, addition of thinners will void Manufacturer's warranty.

APPLICATION

APF CASTORCRETE TC can be spread with a notched squeegee and backrolled with 3/8" roller to achieve the desired coverage rate. When placing the cementitious polyurethane top coat, keep a wet edge between mixes. Place each batch within the working time of the prior one. Failure to do this could result in a visible tie-in line.

SHELF LIFE

One [1] year from date of manufacture, in original unopened container. Store away from heat sources. Store between 50°F and 85°F (10°C – 30°C). Do not allow to freeze. Frozen material is unusable and must be properly disposed of.

LIMITATIONS

- Will yellow and fade from UV exposure.
- Do not apply in direct sunlight.
- Do not apply below 45°F (7.2°C) or above 90°F(32°C).

HANDLING & SAFETY

Avoid contact with skin; wear protective gloves. Application personal must read and fully understand product Safety Data Sheet before using. APF Safety Data Sheets are available at www.apfepoxy.com

APF CASTORCRETE TC PDS 06.02.22

STANDARD WARRANTY STATEMENT

ICP Construction, Inc. ("we" "us" or "our"), manufacturer of Arizona Polymer Flooring, warrants that the product is produced within specifications and is free from defects in material only. No warranty shall be in effect until our Terms and Conditions of Sales (<https://www.icpgroup.com/wp-content/uploads/ICP-Group-Terms-and-Conditions-of-Sale.pdf>) are met, including payment and cooperative promotional considerations. We warrant that the covered product is free of defects in material only and suitable for the specified purpose for a period of one (1) year from the date of shipment, provided the product is (a) installed within its published shelf life, in strict conformance with specifications, and (b) handled, stored, mixed, and applied in accordance with our written instructions. It is your responsibility to initiate any claim against this warranty within the time frame specified below. If we determine that the product meets the requirements of this warranty, then we will, at our sole discretion, either refund the purchase price of the product or provide replacement product, in each case not to exceed the affected area as determined by our authorized technical representative. To obtain replacement or refund you must (a) provide timely written notice to us specifying in detail the non-conformity suspected (no later than five (5) working days after discovery), and (b) provide proof of purchase. We reserve the right to inspect the product prior to replacement. EXCEPT FOR THE EXPRESS WARRANTY ABOVE, THERE ARE NO OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR PURPOSE. IN NO EVENT SHALL WE OR OUR AFFILIATES BE LIABLE FOR ANY INDIRECT, SPECIAL, INCIDENTAL, PUNITIVE, OR CONSEQUENTIAL DAMAGES OF ANY NATURE, REGARDLESS OF THE FORM OF ACTION OR THEORY OF LAW, INCLUDING, WITHOUT LIMITATION, BREACH OF ANY OBLIGATION OR WARRANTY IMPOSED ON US HEREUNDER OR IN CONNECTION HERewith, EVEN IF WE HAVE BEEN ADVISED OF THE POSSIBILITY OF SUCH DAMAGES IN ADVANCE AND EVEN IF A REMEDY SET FORTH HEREIN IS FOUND TO HAVE FAILED OF ITS ESSENTIAL PURPOSE. "CONSEQUENTIAL DAMAGES" SHALL INCLUDE, WITHOUT LIMITATION, LOSS OF USE, INCOME, OR PROFIT, OR LOSSES SUSTAINED AS THE RESULT OF INJURY TO ANY PERSON, OR LOSS OF OR DAMAGE TO ANY PROPERTY (INCLUDING, WITHOUT LIMITATION, PROPERTY HANDLED OR PROCESSED THROUGH THE USE OF THE PRODUCTS), DAMAGES OR LOSSES RESULTING FROM CLAIMS OF OTHER PERSONS AGAINST YOU, OR DAMAGES OR LOSSES SUSTAINED AS THE RESULT OF WORK STOPPAGE, OR REMOVAL AND REPLACEMENT COSTS AND COSTS OF LABOR. IN NO EVENT SHALL OUR LIABILITY ARISING IN CONNECTION WITH OR UNDER THIS WARRANTY (REGARDLESS OF THE FORM OF ACTION OR THEORY OF LAW) EXCEED THE AMOUNT PAID BY YOU FOR THE DEFECTIVE PRODUCT ONLY. THIS LIMITED WARRANTY PROVIDES YOUR EXCLUSIVE REMEDY FOR ANY DEFECT IN THE PRODUCT. If you do not agree with these terms, you may return the product within thirty (30) days of purchase for a full refund, provided the product is not opened, altered, or adulterated in any manner, less any shipping and handling charges of any sort. Use of the product, or retention of the product beyond thirty (30) days, constitutes your acceptance of this limited and exclusive warranty. No customer, distributor, or representative of ours is authorized to change or modify the published data sheets or this warranty in any way. No one is authorized to make oral warranties on behalf of us.