



APPLICATION INSTRUCTIONS: CASTORCRETE RT SYSTEM

MOISTURE VAPOR EMISSION TESTING

All interior concrete floors are subject to possible moisture vapor emission and/or excessive alkalinity that could ultimately cause coating failure. Prior to application, calcium chloride moisture testing should be conducted according to ASTM 1869-04.

SURFACE PREPARATION

Concrete surfaces must be clean, dry and structurally sound. Surface must be shot blasted or scarified to CSP 3 to CSP 5. Keyways must be cut at 1/4" deep by 3/16th wide, 6 inches from all perimeter walls, machinery pedestals, both sides of all control joints, and at regular intervals spaced 10-12 feet apart throughout the flooring system. All floor drains and termination points must have a 1/4" deep by 1/4" wide keyway. Never feather edge CastorCrete™ RT; always turn it into a keyway. Priming of concrete substrates is not usually required under typical circumstances. However, due to variations in concrete quality, surface conditions, surface preparation and ambient conditions, reference test areas are recommended to determine whether priming is required to prevent the possibility of blisters, pinholes and other aesthetic variations. If priming is required, apply Epoxy 100 at the rate of 200-250 sq. ft. per gallon. Proceed with CastorCrete™ RT when primed surface has become tack-free.

MIXING INSTRUCTIONS

Pour entire contents of Parts A, B and C into mixing container and mix for 30 seconds. Then, slowly add Part D (aggregate) over a period of about 15 seconds. Once all of the components are incorporated, mix for an additional 30 seconds. Mixing should be done with a Kohl-type mixer or any other mixer designed to mix heavy mortars. Mixed material should be placed immediately. It is recommended that multiple mixing containers be used to ensure an adequate supply of fresh material.

APPLICATION OF SLURRY

Under normal circumstances, CastorCrete™ RT is applied directly to the concrete without a primer. However, if the concrete is excessively porous, the use of Epoxy 100 as a primer can reduce outgassing, pinholes or blisters. A test area is recommended to determine if a primer should be used. For small areas, CastorCrete™ RT can be metered out and finished with a steel trowel. For large areas, a gauge rake is required. Once the mortar is raked to the desired thickness, immediately role the surface with a looped roller to remove any imperfections and bring the resin to the top. If a non-slip surface is desired, broadcast 24-grit bleached aluminum oxid at a rate of .15 to .25 pounds per square foot. It is very important to keep a wet edge. Each batch must be placed within 10 minutes of the prior one. Failure to do this could result in a visible tie-in line. Allow CastorCrete RT to cure a minimum of 12 hours prior to returning to service.