

SECTION 096280

STAT-REZ PC 350 C STATIC CONTROL FLOORING

PART 1 GENERAL

1.01 SUMMARY

- A. Section includes:
 - 1. Moisture vapor emission testing.
 - 2. Surface preparation.
 - 3. Joint treatment.
 - 4. Furnishing and installation of conductive flooring system.

- B. Related Sections:
 - 1. Section 03300 - Cast-In-Place Concrete:
 - a. Concrete slabs on or below grade shall be installed over an effective moisture vapor barrier.
 - b. Concrete slabs shall be cured 30 days, be structurally sound and have a steel trowel finish.
 - c. Surface shall be well sloped to drains, straight and level with the permissible degree of tolerance of 1/4" in 10'-0" in any direction.
 - d. No curing compounds or surface contaminants shall be used in placing new concrete.

1.02 SYSTEM DESCRIPTION

- A. The flooring system shall consist of a primer coat and a finish coat. Total dry film thickness shall be 25-28 mils.

- B. Finished flooring system shall have the following performance characteristics:
 - 1. Tensile Strength, psi (ASTM D 638)..... 6,230
 - 2. Ultimate Elongation, % (ASTM D 638) 11
 - 3. Compressive Yield Strength, psi (ASTM D 695) 9,850
 - 4. Ultimate Compressive Strength, psi (ASTM D 695) 19,501
 - 5. Ultimate Flexural Strength, psi (ASTM D 790) 9,680
 - 6. Hardness, Shore D (ASTM D 2240) 78
 - 7. Bond Strength to Concrete (ASTM D 4541)..... 350
 - 8. Gloss (60 degrees) 85-90
 - 9. Tabor Abrasion (1000 gm. load 1000 cycles, CS 17 wheel)90 mg. loss
 - 10. Surface Resistance ANSI/ESD 7.1 2.5E4-1E6 ohms
 - 11. Voltage generation, ESD STM 97.2 <15 v
 - 12. Static Decay, 5,000V- 0V < 0.10 seconds

C. Chemical Resistance: (ASTM D-1308 24 HOUR IMMERSION)

Vegetable Oil	no effect
Mustard.....	no effect
Urine	no effect
Gasoline.....	no effect
Motor Oil	no effect
Transmission Fluid	no effect
Brake Fluid.....	slight softening, film recovers
Mineral Spirits	no effect
10% Sulphuric Acid	no effect
10% Hydrochloric Acid	no effect
10% Acetic Acid.....	no effect
Xylene.....	slight softening, film recovers
MEK.....	film destroyed

1.03 SUBMITTALS

- A. Submit manufacturer's product data, literature and brochures.
- B. Submit manufacturer's samples showing color choices and texture.
- C. Submit a statement from the manufacturer indicating the installer's certification.
- D. Prior to commencing work, installer shall prepare two 6" x 6" samples of the resinous flooring chosen for the project showing actual color, thickness and texture. These samples shall serve as a basis for comparison through the duration of the work.

1.04 QUALITY ASSURANCE

- A. All resin material used in this system shall be manufactured by a single manufacturer to ensure compatibility and proper bonding.
- B. Applicator must have a minimum of 3 years experience in installing polymeric flooring systems and be certified by the manufacturer.
- C. All work shall be performed in strict accordance with the manufacturer's written instructions.

1.05 DELIVERY, STORAGE AND HANDLING

- A. All material shall be delivered to the jobsite in unopened containers clearly labeled by the manufacturer and stored in a dry location at a minimum of 65 degrees F.

1.06 WARRANTY

- A. Manufacturer shall guarantee that his materials are free from defects and comply with published specifications.
- B. Applicator shall warranty against faulty workmanship for a period of 3 years from substantial completion of the project.

PART 2 PRODUCTS

2.01 MANUFACTURERS

- A. Resin materials shall be supplied by Arizona Polymer Flooring Inc., Phoenix, Arizona.

2.02 MATERIALS

- A. Primer: 100 percent volume solids epoxy primer.
- B. Ground Plain: 32 percent volume solids conductive epoxy coating
- C. Top Coat : 100 percent volume solids static dissipative Epoxy coating

PART 3 EXECUTION

3.01 EXAMINATION

- A. Verification of Conditions:
 - 1. Inspect surfaces to receive floor system.
 - 2. Conduct calcium chloride moisture vapor emission testing according to ASTM F 1869-04. If test reading is above three pounds, consult Arizona Polymer Flooring before proceeding.
 - 3. Before starting work, report in writing to the Architect any unsatisfactory conditions.
 - 4. Application of any material shall signify that surfaces have been inspected and are satisfactory.

3.02 SURFACE PREPARATION

- A. Surfaces to receive flooring system shall be abraded to a minimum of 5 mil profile using shotblasting or diamond grinding.

3.03 INSTALLATION

- A. Allow sufficient time for the installation of the flooring system. At no time shall the speed of project completion be allowed to detrimentally affect the application.
- B. Provide sufficient light, power, heat and working conditions to permit proper application of the materials. Substrate temperature shall be at a minimum of 50°F during application and for 48 hours thereafter.
- C. Prime prepared substrate with Epoxy 400 at 160 sq. ft. per gallon. Allow to cure overnight before proceeding.
- D. Apply copper tape to at least one grounding point per 1000 square feet.
- E. Apply ground plain coat of Stat-Rez 150 at 250 sq. ft. per gallon
- F. Apply finish coat of Stat-Rez 350 at 100 sq. ft. per gallon.

3.04 FIELD QUALITY CONTROL

- A. Installer shall monitor the thickness of the system as the work progresses. Areas found not to meet the required thickness shall receive additional material until desired thickness is attained.

3.05 PROTECTION

- A. Installation areas must be kept free from traffic and other trades during the application procedure and cure time.

3.06 MAINTENANCE

- A. Floor should be cleaned with ammonia and water or a mild, non-filming detergent. For difficult stains, paint thinner may be used without harming the floor.

END OF SECTION