

PRODUCT DESCRIPTION

APF Oil Stop Primer is a low viscosity, 100% solids resin designed for use as a primer on concrete slabs that are contaminated with hydrocarbons, such as motor oil, solvents, cutting oils and hydraulics fluids but are otherwise sound. It possesses outstanding adhesion and surface tolerance making it ideal for challenging applications such as these.

APF Oil Stop Primer is not recommended for food, beverage, harsh chemical, or routine hot water wash-down applications. Consult APF Technical Service for more information.

USES

- Garages
- Machine Shops
- Warehouse

ADVANTAGES

- Allows application of finish coats to concrete that is moderately contaminated with embedded hydrocarbon based oils

COLORS

Clear, do not add pigment.

PACKAGING

Supplied in complete A+B 1.25 gallon (4.73 L), 25 gallon (94.6 L). Mix ratio 3A : 2B

COVERAGE

100-135 sqft/gallon (12-16 mils WFT)

CONCRETE MOISTURE

It is the applicator's responsibility to test for concrete moisture in accordance with ASTM F2170-19. If moisture is indicated to be more than 85%, apply APF VaporSolve system in accordance with the published system data sheet. Consult APF Technical Service for further information.

TECHNICAL DATA

Mixing Ratio by Volume	3A : 2B
VOC	<50 g/l
Solids Content, by Volume	100%
Tensile Strength (ASTM D-638)	6,230
Ultimate Elongation, (ASTM D-638)	11%
Compressive Yield Strength, (ASTM D-695)	9,850 psi
Flexural Strength, psi (ASTM D-790)	9,680 psi
Cure Time (77°F)	
Dry to Touch	~8 Hours
Recoat	~8 - 24 Hours
Full Cure	~7 Days

Higher temperature and lower humidity will shorten cure time. Lower temperatures and higher humidity will increase cure time.

If 24 hour recoat window exceeded, substrate recoat preparation required.

SURFACE PREPARATION

Concrete must be cured for at least 30 days be clean, structurally sound, and free of wax, loose coatings or curing compounds. Concrete should be properly prepared to achieve a surface Minimum Texture of ICRI/CSP 2-3. Refer to ICRI technical guidelines 310-330 Selecting and specifying concrete surface preparation for sealer, coatings, polymer overlays, and concrete repair. Vacuum the prepared concrete surface to remove all dust. Acid etching is not recommended and will void manufacturers' warranty.

MIXING

Combine components and mix for 2-3 minutes using slow speed drill, scraping the bottom and sides of the mixing container. It is important to NOT whip air into the material while mixing. Material cannot be properly mixed by hand. Apply material immediately after complete mixing.

APPLICATION

Apply material onto surface immediately after mixing with a squeegee, back roll with using a quality solvent resistant 3/8-inch nap roller cover. Apply at a rate of 100-135 sqft/gallon at 12-16 mils WFT. A "wet edge" is recommended when applying product, do not attempt to roll over material that has begun to set. An applicator wearing spiked shoes will back roll the wet material using a quality solvent resistant 3/8-inch nap roller cover to distribute the material uniformly. **The material must be thoroughly rolled twice to achieve optimal substrate wetting {using North-South, East-West Method.}**

Apply a second coat, if necessary, within 24 hour recoat window. If the recoat window is exceeded, the surface must be abraded with 80-100 grit to a uniform gloss free and dust free texture prior to recoat.

LIMITATIONS

- A test patch should always be performed to verify adhesion.
- Do not apply in temperatures below 50°F.
- Coating will yellow when exposed to UV light
- Use of kerosene or propane forced air heating equipment during application may cause discoloration and finish defects.

SHELF LIFE

Part A: 12 months at 50-85°F { 10-30°C }

Part B: 12 months at 50-85°F { 10-30°C }

*When kept at recommended storage conditions and in original unopened containers. DO NOT ALLOW TO FREEZE. Frozen material is unusable and must be properly disposed of.

HANDLING, SAFETY & STORAGE

- Avoid contact with skin; wear protective gloves. Application personnel must read and fully understand product Safety Data Sheet before using. APF Safety Data Sheets are available at www.apfepoxy.com.
- Store away from heat sources. Store between 50°F and 85°F (10°C-30°C). DO NOT FREEZE. Frozen material is unusable and must be properly disposed of.

APF Oil Stop Primer_PDS_07.17.25

STANDARD WARRANTY STATEMENT

ICP Construction, Inc. ("we" "us" or "our"), manufacturer of Arizona Polymer Flooring, warrants that the product is produced within specifications and is free from defects in material only. No warranty shall be in effect until our Terms and Conditions of Sales (<https://www.icpgroup.com/wp-content/uploads/ICP-Group-Terms-and-Conditions-of-Sale.pdf>) are met, including payment and cooperative promotional considerations. We warrant that the covered product is free of defects in material only and suitable for the specified purpose for a period of one (1) year from the date of shipment, provided the product is (a) installed within its published shelf life, in strict conformance with specifications, and (b) handled, stored, mixed, and applied in accordance with our written instructions. It is your responsibility to initiate any claim against this warranty within the time frame specified below. If we determine that the product meets the requirements of this warranty, then we will, at our sole discretion, either refund the purchase price of the product or provide replacement product, in each case not to exceed the affected area as determined by our authorized technical representative. To obtain replacement or refund you must (a) provide timely written notice to us specifying in detail the non-conformity suspected (no later than five (5) working days after discovery), and (b) provide proof of purchase. We reserve the right to inspect the product prior to replacement. EXCEPT FOR THE EXPRESS WARRANTY ABOVE, THERE ARE NO OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR PURPOSE. IN NO EVENT SHALL WE OR OUR AFFILIATES BE LIABLE FOR ANY INDIRECT, SPECIAL, INCIDENTAL, PUNITIVE, OR CONSEQUENTIAL DAMAGES OF ANY NATURE, REGARDLESS OF THE FORM OF ACTION OR THEORY OF LAW, INCLUDING, WITHOUT LIMITATION, BREACH OF ANY OBLIGATION OR WARRANTY IMPOSED ON US HEREUNDER OR IN CONNECTION HERewith, EVEN IF WE HAVE BEEN ADVISED OF THE POSSIBILITY OF SUCH DAMAGES IN ADVANCE AND EVEN IF A REMEDY SET FORTH HEREIN IS FOUND TO HAVE FAILED OF ITS ESSENTIAL PURPOSE. "CONSEQUENTIAL DAMAGES" SHALL INCLUDE, WITHOUT LIMITATION, LOSS OF USE, INCOME, OR PROFIT, OR LOSSES SUSTAINED AS THE RESULT OF INJURY TO ANY PERSON, OR LOSS OF OR DAMAGE TO ANY PROPERTY (INCLUDING, WITHOUT LIMITATION, PROPERTY HANDLED OR PROCESSED THROUGH THE USE OF THE PRODUCTS), DAMAGES OR LOSSES RESULTING FROM CLAIMS OF OTHER PERSONS AGAINST YOU, OR DAMAGES OR LOSSES SUSTAINED AS THE RESULT OF WORK STOPPAGE, OR REMOVAL AND REPLACEMENT COSTS AND COSTS OF LABOR. IN NO EVENT SHALL OUR LIABILITY ARISING IN CONNECTION WITH OR UNDER THIS WARRANTY (REGARDLESS OF THE FORM OF ACTION OR THEORY OF LAW) EXCEED THE AMOUNT PAID BY YOU FOR THE DEFECTIVE PRODUCT ONLY. THIS LIMITED WARRANTY PROVIDES YOUR EXCLUSIVE REMEDY FOR ANY DEFECT IN THE PRODUCT. If you do not agree with these terms, you may return the product within thirty (30) days of purchase for a full refund, provided the product is not opened, altered, or adulterated in any manner, less any shipping and handling charges of any sort. Use of the product, or retention of the product beyond thirty (30) days, constitutes your acceptance of this limited and exclusive warranty. No customer, distributor, or representative of ours is authorized to change or modify the published data sheets or this warranty in any way. No one is authorized to make oral warranties on behalf of us.