

PRODUCT DESCRIPTION

APF Polyaspartic 7500 Low VOC SEMI-GLOSS is a two-component, high-solids, aliphatic Polyaspartic that provides the desirable properties of polyester-polyurethane materials with a shorter cure time and reduced film thickness limitations. This formulation contains a reduced amount of volatile organic compounds (VOC) to comply with environmental regulations.

APF Polyaspartic 7500 Low VOC SEMI-GLOSS is a low viscosity, easy to apply product that results in a very high gloss finish that is both hard and abrasion-resistant. This material releases soil easily and has excellent resistance to a broad range of chemicals. Unlike conventional polyurea materials, **APF Polyaspartic 7500 Low VOC SEMI-GLOSS** has adequate working time to be applied by brush and roller. **APF Polyaspartic 7500 Low VOC SEMI-GLOSS** is a very rapid curing product able to be returned to full service in 24 hours. For exterior applications, an integral UV stabilizer is incorporated to ensure long-term gloss retention and resistance to yellowing.

Developed as a high-performance coating for various protective coatings and seamless flooring applications, **APF Polyaspartic 7500 Low VOC SEMI-GLOSS** is ideally suited for use as a finish coat in color chip and color quartz flooring systems and various types of decorative architectural concrete applications.

USES

- Decorative Quartz and Vinyl Flake Mosaic
- Clean Rooms, Hospital & Healthcare
- Restaurants-Grocery-Food Service
- Automotive
- Aviation
- Pharmaceutical

ADVANTAGES

- Excellent resistance to ultra-violet (UV) light sources
- May be returned to full service in less than 24 hours

CHEMICAL RESISTANCE

Refer to APF Chemical Resistance Chart

TECHNICAL DATA

Mixing Ratio by Volume	1A : 1B
VOC	6 g/l
Solids Content, by Volume	75%
Hardness, Pendulum	172
Gloss (60°)	60-90
Bond Strength to Concrete (ASTM D-4541)	>350 psi, concrete fails
Cure Time (77°F)	
	Dry to Touch ~1 Hour
	Light Traffic ~4 Hours
	Vehicle Traffic ~24 Hours
	Full Cure/Full Chemical Resistance ~72 Hours

Cure times are dependent on temperature and humidity

COLORS

10 Standard colors & clear available. Use only APF Polyaspartic pigment packs (01-CPAPP xxx-x).

PACKAGING

Supplied in complete A+B 1.0 gallon (3.7 L), 10 gallon (37.8 L).
Mix ratio 1A : 1B

SURFACE PREPARATION

Concrete must be cured for at least 30 days and be clean, structurally sound, and free of wax, loose paint or curing compounds. Concrete should be shot blasted to achieve a surface minimum texture of ICRI 3 - 4. Refer to ICRI Technical Guidelines 310-330 *Selecting and Specifying Concrete Surface Preparation for Sealers, Coatings, Polymer Overlays, and Concrete Repair*. Acid etching is not recommended and will void Manufacturer's warranty. Carefully follow the guidelines listed in the Arizona Polymer Flooring published application instructions available at www.apfepoxy.com. Vacuum prepared concrete surface to remove all dust. Previously coated surfaces that are soundly adhered must be mechanically cleaned and abraded to achieve uniformly gloss-free, open texture.

MIXING

APF POLYASPARTIC 7500 Low VOC SEMI-GLOSS is packaged in premeasured and bulk units. Proper proportioning and homogenization are critical for success. Mixing ratio is 1A : 1B. Premix both components for 3 minutes prior to blending. Do not attempt to hand mix. Be sure to move the drill around the mixing container scraping the sidewalls and bottom.

Add color pack if required to A component and blend thoroughly before adding B component. Bone-117, Safety Blue-077, Safety Red-083, Safety Yellow-063 & White-000 require 1 quart color pack loading for adequate hiding and coverage.

Add component B to component A and mix with medium speed drill mixer for three [3] minutes. Distribute material immediately after complete mixing.

APPLICATION

Polyaspartic 7500 Low VOC SEMI-GLOSS is a very reactive material and requires special application techniques. APF POLYASPARTIC 7500 Low VOC SEMI-GLOSS is applied by roller, brush and squeegee. For detailed installation instructions, see Arizona Polymer Flooring application manual.

Polyaspartic 7500 Low VOC SEMI-GLOSS is a very reactive material and requires special application techniques. It may be brushed, rolled, or sprayed using plural component spray equipment. Easy application is accomplished by pouring the freshly mixed product on the floor, spreading to the desired thickness with a rubber squeegee, and finish rolling immediately with an 18-inch roller. The mechanic rolling the material should wear spiked shoes to walk on the wet material. Because the material sets quickly, change roller covers every hour, or less at increased temperatures.

APPLICATION, cont.

Mixed material must be spread immediately after mixing. On large jobs, be sure to have enough workforce to maintain a wet edge. Do not apply at more than 10 mils. **Product applied at greater than 10 mils (<160 ft²/Gal) will generate excessive CO₂ and result in surface defects.**

CONCRETE MOISTURE

Test for concrete moisture in accordance with ASTM F2170–19. If moisture is indicated to be in excess of 85%, apply APF Vapor-Solve® system in accordance with the published technical data sheet. Consult APF Technical Service for further information.

LIMITATIONS

- Not suitable for constant temperature exposure over 175°F (80°C)
- Prior to application, measure and confirm that ambient temperature and humidity conditions are at least 5°F over dew point.
- Do not exceed 10 mils wet film thickness, surface defects will occur.

SHELF LIFE

One [1] year from date of manufacture, in original unopened container. Store away from heat sources between 50°F and 85°F (10°C – 30°C).

HANDLING & SAFETY

Use only with adequate ventilation. Appropriate cartridge-type respirator must be used during application in confined areas. Avoid contact with skin; wear protective gloves. User must read and understand Safety Data Sheet before using. APF Safety Data Sheets are available at www.apfepoxy.com



APF POLYASPARTIC 7500 LOW VOC SEMI-GLOSS FINISH

PRODUCT DATA SHEET

THIS PAGE INTENTIONALLY BLANK

APF POLYASPARTIC 7500 Low VOC SEMI-GLOSS 01.04.24

STANDARD WARRANTY STATEMENT

ICP Construction, Inc. ("we" "us" or "our"), manufacturer of Arizona Polymer Flooring, warrants that the product is produced within specifications and is free from defects in material only. No warranty shall be in effect until our Terms and Conditions of Sales (<https://www.icpgroup.com/wp-content/uploads/ICP-Group-Terms-and-Conditions-of-Sale.pdf>) are met, including payment and cooperative promotional considerations. We warrant that the covered product is free of defects in material only and suitable for the specified purpose for a period of one (1) year from the date of shipment, provided the product is (a) installed within its published shelf life, in strict conformance with specifications, and (b) handled, stored, mixed, and applied in accordance with our written instructions. It is your responsibility to initiate any claim against this warranty within the time frame specified below. If we determine that the product meets the requirements of this warranty, then we will, at our sole discretion, either refund the purchase price of the product or provide replacement product, in each case not to exceed the affected area as determined by our authorized technical representative. To obtain replacement or refund you must (a) provide timely written notice to us specifying in detail the non-conformity suspected (no later than five (5) working days after discovery), and (b) provide proof of purchase. We reserve the right to inspect the product prior to replacement. EXCEPT FOR THE EXPRESS WARRANTY ABOVE, THERE ARE NO OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR PURPOSE. IN NO EVENT SHALL WE OR OUR AFFILIATES BE LIABLE FOR ANY INDIRECT, SPECIAL, INCIDENTAL, PUNITIVE, OR CONSEQUENTIAL DAMAGES OF ANY NATURE, REGARDLESS OF THE FORM OF ACTION OR THEORY OF LAW, INCLUDING, WITHOUT LIMITATION, BREACH OF ANY OBLIGATION OR WARRANTY IMPOSED ON US HEREUNDER OR IN CONNECTION HERewith, EVEN IF WE HAVE BEEN ADVISED OF THE POSSIBILITY OF SUCH DAMAGES IN ADVANCE AND EVEN IF A REMEDY SET FORTH HEREIN IS FOUND TO HAVE FAILED OF ITS ESSENTIAL PURPOSE. "CONSEQUENTIAL DAMAGES" SHALL INCLUDE, WITHOUT LIMITATION, LOSS OF USE, INCOME, OR PROFIT, OR LOSSES SUSTAINED AS THE RESULT OF INJURY TO ANY PERSON, OR LOSS OF OR DAMAGE TO ANY PROPERTY (INCLUDING, WITHOUT LIMITATION, PROPERTY HANDLED OR PROCESSED THROUGH THE USE OF THE PRODUCTS), DAMAGES OR LOSSES RESULTING FROM CLAIMS OF OTHER PERSONS AGAINST YOU, OR DAMAGES OR LOSSES SUSTAINED AS THE RESULT OF WORK STOPPAGE, OR REMOVAL AND REPLACEMENT COSTS AND COSTS OF LABOR. IN NO EVENT SHALL OUR LIABILITY ARISING IN CONNECTION WITH OR UNDER THIS WARRANTY (REGARDLESS OF THE FORM OF ACTION OR THEORY OF LAW) EXCEED THE AMOUNT PAID BY YOU FOR THE DEFECTIVE PRODUCT ONLY. THIS LIMITED WARRANTY PROVIDES YOUR EXCLUSIVE REMEDY FOR ANY DEFECT IN THE PRODUCT. If you do not agree with these terms, you may return the product within thirty (30) days of purchase for a full refund, provided the product is not opened, altered, or adulterated in any manner, less any shipping and handling charges of any sort. Use of the product, or retention of the product beyond thirty (30) days, constitutes your acceptance of this limited and exclusive warranty. No customer, distributor, or representative of ours is authorized to change or modify the published data sheets or this warranty in any way. No one is authorized to make oral warranties on behalf of us.



150 Dascomb Rd., Andover, MA 01810 • 1.866.667.5119 • icpgroup.com
©2024 APF Polymer Surfaces and other marks on this brochure are trademarks of ICP

For more information,
please visit us at apfepoxy.com